



HMP MINERALS PVT LTD

Corporate Office: 111, Industrial Area, Sion (E), Mumbai-400 022, India
Tel: +91 22 24090124/127, E-mail: sales@hmpindia.com Website: www.hmpindia.com

ACTIVATED MANGANESE DIOXIDE POWDER

Typical Characteristic	
• Assay as MnO ₂ %	70 ± 2
• Available Oxygen %	13 ± 0.5
• Loss on Drying (at 120°C for 2 hrs.) %	≤5 %
• pH Value (10% aq.Soln.)	9.5 – 12.0
• Alkanity (as NaOH)	0.4 – 3.0 %

- It is used to make Activated Manganese Dioxide Paste for the use in Polysulfide Sealant. It acts as “Accelerator” and helps to ‘set’ when mixed with “Base” component. It forms rubberized mass and helps to seal the joints and gap.
- Material as per buyer’s specification can also be made available.

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products, herein described, nor do we accept any liability for loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our products prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.